

## URECO PTC

90% SOLID POLYASPARTIC / POLYUREA TOP COAT

GLOSS FINISH

TDSPTCEN.V01

# BEYOND FLOORS...

### PRODUCT DESCRIPTION

URECO PTC is a 90% solid Polyaspartic / Polyurea clear two components coating system. URECO PTC is also a self-priming so it can be used as a primer as well as a protective coating. The fast curing of this product and its fast turnaround allow the installation of a flooring system in one day. Surface finish can be various skid resistance textures (sold separately).

### BENEFITS

- UV color change resistant, non yellowing
- Interior and exterior use
- Hard and flexible with good elongation for dynamic concrete protection
- VOC Compliant
- Easy application, easy 1 to 1 mixing ratio
- Fast curing with good pot life allows for 2-3 coat application for single day installation
- Excellent curing capability at very low temperature
- Durable, impermeable, seamless and esthetic
- Superior gloss and gloss retention
- Good chemical and impact resistance
- Easily cleaned, maintained and a more sanitary work environment
- Meets Canadian Food Inspection Agency

### COLORS

Clear

### TYPICAL USES

- For exterior and interior use
- Garages commercial and residential
- Basements, cold cellars, access ways, entry ways and staircases
- Retail store, commercial centers and boutiques
- Aircraft Hangars, automobile dealerships, car washes and wash ways
- Medium duty traffic areas
- Area requiring high esthetic appearances, pleasing, durable coatings for concrete floors
- Pharmaceutical and aerospace
- Hospitals, and schools
- Industrial showrooms and office buildings

### TECHNICAL INFORMATION

|                       |  |
|-----------------------|--|
| Color                 | Clear  |
| Cure Time @ 22°       |  |
| Working time          | 15-20 minutes  |
| Tack free             | 1-2 hours  |
| Hard dry              | 2-4 hours  |
| Foot traffic          | 2-4 hours  |
| Light traffic         | 24-48 hours  |
| Heavy traffic         | 48-72 hours  |
| Full cure             | 10-14 days   |
| Mix Ratio (by volume) | 2 component kit<br>1 Part A (resin)<br>1 Part B (hardener)                                       |
| Coverage              |  |
| Clear and colored     | 1 <sup>st</sup> coat: 10-15 (107-160 sqft/gal)<br>2 <sup>nd</sup> coat: 10-15 (107-160 sqft/gal) |
| Pot Life @ 25°C       | 15-20 minutes<br>Pot life is shorter at higher temperature                                       |
| Solid by weight       | 90   |
| Toxicity              | When cured<br>Non-toxic<br>Non tainting  |

### PHYSICAL PROPERTY

### TEST METHOD

### RESULT

|  |             |                                  |
|--|-------------|----------------------------------|
| Adhesion to concrete<br>CS17 / 1000 Cycles / 1000g           | ASTM-4060   | 0.050g                           |
| Bond Strength  | ASTM D-4541 | > 500 psi<br>(substrate failure) |
| Coefficient of Friction<br>Standard Slip Resistant<br>Smooth | ASTM D-2047 | 0.7<br>0.9                       |
| Hardness (Shore D)   | ASTM D-2240 | 70                               |
| Elongation   | ASTM D638   | 50%                              |
| VOC Content  |             | > 50 g/l                         |

### POWERBLAST CANADA

3505 Le Corbusier Blvd., Laval, QC, H7L 4Z4

1-866-975-1133

www.powerblastcanada.com

LIKE & FOLLOW US ON SOCIAL MEDIA!



Facebook.com/powerblastcanada



Linkedin/powerblastcanada



Instagram.com/urecoflooring

### URECO PTC

90% SOLID POLYASPARTIC / POLYUREA TOP COAT

GLOSS FINISH

TDSPTCEN.V01

## BEYOND FLOORS...

#### PACKAGING

URECO PTC is available in 2 gallons / kit. All kits containing 1 part A of resin and 1 part B hardener.

#### SURFACE PREPARATION

Surface preparation is required. Substrate must be profiled, dry, clean, oil free, and sound. Use Ureco Degreaser to remove all contaminants (oils, greases and others). Remove any dust, laitance, dirt, curing agent impregnations, wax, foreign matter, coatings and others from the surface by an appropriate mechanical to achieve a profile equivalent to ICRI CSP 2-3 with Blastrac and/or diamond grinder with dust free collector. Need proper bonding to the substrate. Call the Technical Department for preparation recommendation.

#### PRIMING

Self-primer

#### MIXING

##### CLEAR AND COLORED VERSION

Pre-mix each component separately. Empty 1 part of component B with 1 part component A, (**mixing ratio 1 for 1**) into an appropriate mixing container. Mix the combined components for at least 2-3 minutes using a low-speed drill (300-450 rpm) to minimize entrapping air in the system. When completely mixed, the product should be uniform in color and consistency.

#### APPLICATION

URECO PTC is applied with a flat squeegee and then back roll with a high quality 10mm lint free or microfiber roller to obtain a uniform coating.

NOTE: Sanding between coats is required to ensure bonding.

#### CLEANING

This product is considered to be a low maintenance flooring solution; however, certain textures and service environments do require certain procedures. Please refer to the "Maintenance Recommendation".

#### STORAGE CONDITIONS

URECO PTC must be stored in a dry cool place between 15°C and 21°C. Do not allow to freeze. The shelf life of this product is 6 months from ship date in the original unopened container. Do not store near open flame.

#### CHEMICAL RESISTANCE

This product is resistant to many common chemicals. Please call the Technical Department for actual resistance to specific chemical/agents.

#### MOISTURE CONCERNS

Moisture vapor transmission in the slab should be measured prior to application of polymeric systems to ensure a long lasting, durable installation.

#### LIMITATIONS

This product is best suited for application in temperatures between 4°C and 30°C. Substrate must be clean, sound and dry. Substrate temperature must be a minimum of 10°C and must be 3°C (5.5F) above measured dew point. Maximum relative humidity is 85% moisture content of the substrate must less than 4% when coating is applied. Ambient humidity during application and curing must be minimum 30% maximum 75%. Do not apply to surfaces where moisture vapor can condense and freeze or to porous surfaces where moisture vapor transmission will occur during the application. Do not apply in areas where the humidity is greater than 85%. Freshly applied material should be protected from dampness, condensation and water for at least 24 hours. Beware of air flow and changes in air flow. Introduction of dust, debris, and particles etc. May result in surface imperfections and other defects. If you have any questions, please contact the PowerBlast Canada Technical Services at 1-866-975-1133.

#### CAUTION

Workers should wear protective clothing consisting of splash-proof goggles, impermeable gloves and, where exposure limits are exceeded, organic vapor respirators. Follow the Safety Data Sheet (SDS) for proper personal protective equipment to use when handling this product. Use only as directed. **KEEP OUT OF REACH OF CHILDREN.**

**IMPORTANT NOTICE-** All statements, recommendations and technical information contained in this document are based on tests and information, which PowerBlast Canada believes to be accurate as of this date. The buyer should test this product before use. PowerBlast Canada assumes no obligation or liability for results obtained from the use of this product. The product and information herein are furnished at the buyers request and risk. PowerBlast Canada will not be liable for any direct, indirect, consequential, economic or any other damage whatsoever except to replace the product and or refund the purchase price to the purchaser.

#### POWERBLAST CANADA


3505 Le Corbusier Blvd., Laval, QC, H7L 4Z4


1-866-975-1133

[www.powerblastcanada.com](http://www.powerblastcanada.com)

LIKE & FOLLOW US ON SOCIAL MEDIA!

 [Facebook.com/powerblastcanada](https://www.facebook.com/powerblastcanada)

 [Linkedin/powerblastcanada](https://www.linkedin.com/company/powerblastcanada)

 [Instagram.com/urecoflooring](https://www.instagram.com/urecoflooring)